

TYPE S (Mortar Cement : Sand)

1. PRODUCT NAME

SPEC MIX® Type S Mortar

2. MANUFACTURER



Quikrete Chicago

1S950 South Lorang Road
Elburn, IL 60119
Phone: (630) 557-8252
Fax: (630) 557-8270

3. PRODUCT DESCRIPTION

General

-The material properties of mortar, which influence the structural performance of masonry, are compressive strength, bond strength and elasticity. Because the compressive strength of masonry mortar is less important than bond strength, workability and water retentivity, the latter properties should be given principal consideration in mortar selection. Mortar should be selected based on the design requirements and with due consideration of the MSJC Code and specification provisions affected by the mortar selected.

Basic Use

-Type S mortar is recommended for use in reinforced masonry, unreinforced masonry where maximum flexural strength is required, and where mortar adhesion is the sole bonding agent between facing and backing.

-Type S is a reasonably high compressive strength mortar which tests indicate has a high tensile bond strength with most brick units.

Composition and Materials

-Mortar Cement (ASTM C 1329)
"Standard Specification for Mortar Cement"
-Masonry Aggregate (ASTM C 144)
"Standard Specification for Aggregate for Masonry Mortar"

Colored Mortar

-PCI uses only the highest quality pigments available providing the strongest and most stable colors. In order to consistently achieve the desired mortar color, PCI incorporates the pigment into the mortar during the factory blending process. All ratios of the dry components remain constant in every batch.

-Custom matching can be performed to attain a match to a specific sample.

-Colored mortar is to be discarded two hours after initial mixing.

-Do not retemper colored mortar

4. INSTALLATION

Mixing

-All cementitious materials and aggregate shall be mixed between 3 and 5 minutes in a mechanical batch mixer with the maximum amount of water to produce a workable consistency.

-Hand mixing of the mortar is permitted with the written approval of the specifier outlining hand-mixing procedures.

Average Coverage

Unit Size	Units/3000#
Standard Brick	1550
Queen Sized Brick	1315
King Sized Brick	1160
Utility Brick	1000
4" Block	600
6" Block	450
8" Block	420
12" Block	395

Limitations

-Mortar type should be correlated with the particular masonry unit to be used because certain mortars are more compatible with certain masonry units.

-The specifier should evaluate the interaction of the mortar type and masonry type and masonry unit specified. That is, masonry units having a high initial rate of absorption will have greater compatibility with mortar of high-water retentivity.

Testing

-Test method C 780 is acceptable for preconstruction and construction evaluation of mortars for plain and reinforced unit masonry.

-There is no ASTM method for determining the conformance or nonconformance of a field mortar prepared to the property specification of specification C 270.

-Compressive strength values resulting from field tested mortars do not represent the compressive strength of mortar as tested in the laboratory nor that of the mortar in the wall. Physical properties of field sample mortars shall not be used to determine compliance to the ASTM C 270 intended as criteria to determine the acceptance or rejection of the mortar.

Retempering

-Mortars that have stiffened because of evaporation of water from the mortar shall be retempered. Mortars shall be used and placed in final position within 2 1/2 hours after initial mixing.

5. LEED INFORMATION

Applicable Credits:

- MR Credit 4.1
- MR Credit 4.2
- MR Credit 5.1
- MR Credit 5.2
- Pre Consumer Recycled Content 4.3%
- Local Harvest Content..... 77%
- Production Location
City..... Elburn
State..... Illinois
Zip.....60119
- 100% harvested w/in 500 miles

TYPE S (Mortar Cement : Sand)**6. TECHNICAL DATA****Applicable Standards**

- ASTM C 270, "Standard Specification for Mortar for Unit Masonry."
- ACI 530 "Building Code Requirements for Masonry Structures"
- ACI 530.1 " Specification for Masonry Structure"

ASTM C 270, TEST RESULTS FOR PCI TYPE S MORTAR

28 day strength	2,293 psi
Water retention.....	89.00 %
Initial Flow	110 %
Final Flow.....	98 %
January 24, 2005	

ACI 530**-Mortar References:**

- Part 1 (General)
 - Section 1.5 Compressive Strength of Masonry (f' m)
 - Table 1 and table 2
- See PCI Compressive Strength of Masonry Tests**
- Part 2 (Products)
 - References ASTM C 270
- See PCI Mortar Data Sheet**

7. TECHNICAL SERVICES**Quikrete Chicago**

1S950 South Lorang Road
Elburn, IL 60119
(630) 557-8252

8. SAFETY/HEALTH

- Refer to M.S.D.S. for safety/health information.

9. WARRANTY

SPEC MIX, Inc warrants this product to be of merchantable quality when used or applied in accordance with the instructions hereon. This product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is LIMITED to the replacement of the product (as purchased) if found to be defective, or at the shipping companies' option, to refund the purchase price. All claims under this warranty must be written and submitted to SPEC MIX, Inc.